



The Biofore Company **UPM**



## New Kraft Special Stabilized backing for Digital SRA3/ SRA3+ film products

Introducing the **KRAFT SPECIAL STABILIZED 120 (FGX)** backing for our Digital SRA3/  
SRA3+ film products. This new backing upgrades and replaces our KRAFT SPECIAL STABILIZED  
100 (E1), and is designed for maximum printing efficiency with optimal results.

The thickness of this backing material has increased from 97 to 112 microns for improved  
runnability in digital printing machines. Excellent lay-flat properties provide consistently reliable  
print runs even at the highest speeds and compact stacking in printer trays.

- Tested for top performance with SRA3/SRA3+ sheet sizes, in medium and high volume printers
- High dimensional stability for reliable feed-through, further improved compared to the KSS100 backing
- Good lay-flat properties for efficient stacking in trays before and after printing

Backing comparison	Kraft Special Stabilized 100 (E1)	Kraft Special Stabilized 120 (FGX)
Weight (g/m <sup>2</sup> )	100	120
Thickness (µm)	97	112
Tensile strength MD (kN/m)	7.0	8.0
Tensile strength CD (kN/m)	3.7	4.0

For further information, please contact your UPM Raflatac Area Sales Manager and/or Customer Service.

**UPM RAFLATAC**

# UPM RAFLATAC TECHNICAL INFORMATION

08/2016 ENG 3862

SELF-ADHESIVE	SHEETS
BACKING	KRAFT SPECIAL STABILIZED 120
Kraft	FGX (sales code)
Product	White woodfree kraft backing paper
Use	A4 applications for laser end-use where high layflat is demanded.

## Typical technical values

Substance	120	g/m <sup>2</sup>	ISO 536
Caliper	112	µm	ISO 534
Tensile strength MD	8.0	kN/m	ISO 1924
Tensile strength CD	4.0	kN/m	ISO 1924

**Advantages** High dimensional stability providing superior lay-flatness. Specially developed for SOHO, medium and high volume laser printers.

**Disclaimer** The performance of the product should always be tested in the actual application conditions. Our recommendations are based on our most current knowledge and experience. As our products are used in conditions beyond our control, we cannot assume any liability for damage caused through their use. Users of our products are solely responsible that the product is suitable for its intended application, and have determined such at their sole discretion. Users must comply with any applicable legislation and/or testing requirements for the finished article, and are responsible for bringing their products to market.

This publication does not constitute any warranty, express or implied, and is intended only for the recipient and cannot therefore be transferred to any third party. We cannot assume any liability for the use of our products in conjunction with other materials.

All our products are sold subject to UPM Raflatac's general sales conditions, and you should ensure that any existing laws are observed.

This publication replaces all previous versions. All information is subject to change without notice.

