



## SR 24 Longer-lasting removability on surfaces from glass to cardboard

SR 24 introduces the latest adhesive technology for excellent long-term removability with UPM Raflatac paper sheet products. High initial tack on surfaces from glass to cardboard means this one adhesive covers a wide range of removable labelling needs.

Minimal adhesive residue on-press and good die-cutting properties reduce maintenance downtime and support productivity in conversion. And with SR 24's new anti-ageing formulation, you can stock with confidence, reduce waste, and respond to the fastest lead times.

- Excellent initial adhesion and long-term removability
- New anti-aging formulation for increased shelflife
- New low-odour formulation
- ISEGA approval for direct contact with dry, moist and non-fatty foodstuffs

Face quality (Sales code)		Sales code	Sheet size (cm)	No-score backprint (W1)	Score backprint (W3)	Package size sheets per ream
Vellum-FSC (CKG)	Old code	CKG SR21 14	50 x 70	7127736	7127743	250
	New code	CKG SR24 14	50 x 70	7151984	7151991	250
Raflacoat Plus-FSC (BUK)	Old code	BUK SR21 14	50 x 70	7127903	7127910	250
	New code	BUK SR24 14	50 x 70	7152004	7152011	250
Raflagloss-FSC (CKH)	Old code	CKH SR21 14	50 x 70		7128078	250
	New code	CKH SR24 14	50 x 70		7152028	250
Castgloss-FSC (DFW)	Old code	CFW SR21 14	50 x 70		7128177	250
	New code	CFW SR21 14	50 x 70		7152035	250

# UPM RAFLATAC TECHNICAL INFORMATION

02/2015 ENG 654

<b>ADHESIVE</b>	<b>SR 24</b>
Removable	SR24 (sales code)
Type	Removable adhesive for sheets.
Composition	Acrylic, water borne.
Use	A general purpose removable adhesive designed for sheets laminates. Good long-term removability. Good cohesion and adhesion at difficult substrates.

## Typical technical values

Tack min	3	N	FTM9
Shear min	6	h	FTM8
Labelling temperature min	5	°C	
Service temperature min	0	°C	
Service temperature max	80	°C	
Limitations	Not recommended for labelling PVC or acrylic coated surfaces, long term removability might be restricted.		
Approvals	The research centre ISEGA has given the adhesive approval for dry, moist and non-fatty foodstuff.		
Shelf life	From the date of manufacture 2 years at +20 deg C and RH 50%. Prolonged storage at higher temperatures and/or humidity levels will shorten the shelf life.		

## Disclaimer

Our recommendations are based on our most current knowledge and experience. As our products are used in conditions beyond our control, we cannot assume any liability for damage caused through their use. This publication replaces all previous versions. All information is subject to change without notice.

