



New Coated Board face

Our new Coated Board 135-FSC (FHQ) is designed for applications requiring labels with a higher level of stiffness than standard solutions.

This 135 g/m² FSC-certified label face is suitable for uses including premium promotional labels, point-of-sale promotional displays and wall decoration labels.

Coated Board 135-FSC (FHQ) provides an intermediate weight and stiffness between our label faces of 80 g/m² and 180 g/m².

Combination	Sales code (permanent adhesive)	Size (cm)	Packaging (reams)	MOQ	Sheet EAN code
				Wrapped	Solid, unprinted backing (W0)
Coated Board 135-FSC	FHQ/SP34/14/W0	50 x 70	250	5000	7161587
		100 x 70	125	2500	7161594

For further information, please contact your UPM Raflatac Area Sales Manager and/or Customer Service.

UPM RAFLATAC TECHNICAL INFORMATION

09/2016 ENG 3898

SELF-ADHESIVE SHEETS

FACE	COATED BOARD 135-FSC
Board	FHQ (sales code)
Product	Premium silk coated wood free paper. Consistently high quality, realistic printing results and vibrant images.
Use	General board uses where high stiffness is required like premium promotional labels/stickers, self-adhesive trading cards, wall decoration labels and point-of-sales promotional displays.

Typical technical values

Substance	135	g/m ²	ISO 536
Caliper	135	µm	ISO 534
Brightness	100	%	ISO 2470
Roughness	1.6	µm	ISO 8791-4
Opacity	96	%	ISO 2471
Gloss	35	%	Hunter 75°
CIE Whiteness	127	%	ISO 11475
Printability	Sheet feed offset.		
Sustainability	The product named as FSC is registered to SGSCH-COC-004879 FSC™ Mix credit.		

Disclaimer The performance of the product should always be tested in the actual application conditions. Our recommendations are based on our most current knowledge and experience. As our products are used in conditions beyond our control, we cannot assume any liability for damage caused through their use. Users of our products are solely responsible that the product is suitable for its intended application, and have determined such at their sole discretion. Users must comply with any applicable legislation and/or testing requirements for the finished article, and are responsible for bringing their products to market.

This publication does not constitute any warranty, express or implied, and is intended only for the recipient and cannot therefore be transferred to any third party. We cannot assume any liability for the use of our products in conjunction with other materials.

All our products are sold subject to UPM Raflatac's general sales conditions, and you should ensure that any existing laws are observed.

This publication replaces all previous versions. All information is subject to change without notice.

